

Nicoflex[®] 1000 Specification

Reinforced LDPE Geomembrane.

TEST	UNIT	Nicoflex 1000	TEST METHOD
Weight	g/m ²	1133	EN 965
Thickness at 2kPa _(overall)	mm	1.35	EN 964-1
Scrim Reinforcing		PET	
Coating material		HSPO	
Nominal Tensile Strength (CMD & MD)	kN/m	24	EN 13859
Elongation at NTS (MD)	%	12.5	EN 13859
Elongation at NTS (CMD)	%	17	EN 13859
Tear Resistance (CMD & MD)	N	400	DIN 53363
Length	m	100	
Width	m	2.05	
Diameter of roll	m	0.45	
Weight of roll	kg	240	

Issue 6 - Jan 11