

## Nicoflex<sup>®</sup> 800 Specification

Reinforced LDPE Geomembrane.

TEST	UNIT	Nicoflex 800	TEST METHOD
Weight	g/m <sup>2</sup>	970	EN 965
Thickness at 2kPa <sub>(overall)</sub>	mm	1.2	EN 964-1
Scrim Reinforcing		PET	
Coating material		HSPO	
Nominal Tensile Strength (CMD & MD)	kN/m	24	EN 13859
Elongation at NTS (MD)	%	12.5	EN 13859
Elongation at NTS (CMD)	%	17	EN 13859
Tear Resistance (CMD & MD)	N	400	DIN 53363
Length	m	100	
Width	m	2.05	
Weight of roll	kg	205	

Issue 6 - Jan 11