

## Nicotarp<sup>®</sup> 7 Specification

TEST	UNIT	Nicotarp 7	TEST METHOD
Weight	g/m <sup>2</sup>	190	NEN-EN 965
Thickness at 2kPa	mm	0.3	DIN 53353
Core material		HDPE	
Coating material		LDPE	
Tensile strength MD	N/5 cm	850	ISO 1421
Tensile strength CD	N/5 cm	850	ISO 1421
Elongation at break MD	%	30	ISO 1421
Elongation at break CD	%	20	ISO 1421
Length	m	100	
Width	m	2.0	
Diameter of roll	cm	20	
Weight of roll	kg	39	

Issue 3 - Jan08