

PAG 6 Geocomposite- Fully Wrapped

Consists of a cusped HDPE (High Density Polyethylene) core former, thermally bonded to a geotextile filter

PROPERTIES	MD/CD	UNIT	VALUE	STANDARD
Composite				
In Plane gas flow			@ 7mm	
At 100kPa		l/m.s	2.4	
At 250kPa		l/m.s	2.1	
			@ 3mm	
At 100kPa		l/m.s	0.8	
At 250kPa		l/m.s	0.6	
With soft foam contact surfaces to simulate textile intrusion into the core due to soil pressure				
Ventilation free path		(mm ² /m)	2200	(indicative)
Air Volume		(l/m ²)	3.3	(indicative)
Equivalent Void Depth		(mm)	3.3	(indicative)
Thickness at 2kPa		mm	7.0	EN ISO 9863-1
Mass per unit area		g/m ²	790	EN ISO 9864
Tensile strength	MD	kN/m	24	EN ISO 10319
	CD	kN/m	15	EN ISO 10319
Elongation at Peak	MD	%	50	EN ISO 10319
	CD	%	40	EN ISO 10319
Static puncture resistance CBR		N	3750	EN ISO 12236
Geotextile				
Thickness at 2kPa		mm	1.2	EN ISO 9863-1
Tensile strength	MD	kN/m	9.5	EN ISO 10319
	CD	kN/m	9.5	EN ISO 10319
Pore size O ₉₀		µm	115	EN ISO 12956
Static puncture resistance CBR		N	1600	EN ISO 12236
Dynamic perf cone drop		Mm	32	EN ISO 13433
Roll size	Width	m	1.1	
	Length	m	50	

Jan 2017