

PAG Protective Fleece (300 GSM)

PROPERTIES	MD/CD	UNIT	VALUE	STANDARD
Static puncture strength(CBR)		kN	2.5	BS EN ISO 12236
Push-through displacement		mm	75	BS EN ISO 12236
Tensile strength	MD	kN/m	15	EN ISO 10319
	CD	kN/m	15	EN ISO 10319
Tensile elongation	MD	%	80	BS EN ISO 10319
	CD	%	80	BS EN ISO 10319
Cone Drop		mm	10	BS EN 13433
Thickness	2kPa	mm	3.5	BS EN ISO 9863-1
Apparent Pore Size 90% finer		μm	150	EN ISO 12956
Waterflow		l/s/m ²	100	EN ISO 11058
Coefficient of permeability		m/s x10 ⁻³	7.0	EN ISO 11058
Resistance to weathering (UV) @ 50MJ/m ² (1-4 months depending on location/season)		RETAINED STRENGTH	>90%	EN12224
Standard Roll Length		m	100	
Standard roll width		m	2 or 6	
Roll weight		kg	60 or 180	



1st June 2011