

Technical Data Sheet – PAG 25 Single & Fully wrapped

(Rev. Mar 2023)

Geocomposite venting layer suitable for use in all ground gas applications.

**Vacuum formed HDPE core
Bonded to
Geotextile fabric**



- Proven performance in sub slab venting applications
- Available single textile or full wrapped
- Supplied in rolls for efficient installation

Description:

PAG 25 is manufactured from a single layer of vacuum formed high density polyethylene (HDPE) bonded to a layer of geotextile fabric. It acts as a high performance venting layer beneath building slabs for the efficient dilution and dispersion of ground gases. Developed in the early 1980's as a drainage composite, PAG 25 has been used for over 25 years as a means of venting beneath buildings. PAG 25 is supplied rolled and must be turned over and installed white textile side down to act as a ground gas ventilation blanket. (See above image).

Applications:

PAG 25 is suitable for all sites where the Risk Assessment defines as appropriate sub slab ventilation.

Approvals & Standards:

- BS8485:2015+A1:2019 – Code of practice for the design of protective measures for methane and carbon dioxide ground gases for new buildings.
- CE Mark EN 13252:2016 – Geocomposite for drainage applications.



System Components:

- All PAG venting components
- All PAG gas barriers
- PAG SAGR - Self Adhesive Gas Resistant Membrane
- PAG Cross Linked Butyl Sealant
- PAG Primer

Technical Data: PAG 25 Single & Fully Wrapped

PROPERTIES	MD/CD	UNIT	VALUE	STANDARD
Composite				
In Plane gas flow At 20kPa		l/m.sec	9.0	ASTM D4716
With soft foam contact surfaces to simulate textile intrusion into the core due to soil pressure				
Ventilation free path		mm ² /m	11500	Indicative
Air volume		l/m ²	18.9	Indicative
Equivalent Void Depth		mm	18.9	Indicative
Thickness at 2kPa		mm ±10%	26.2 SW 27.4 FW	EN ISO 9863-1
Mass per unit area		g/m ²	1670 SW 1790 FW	EN ISO 9864
Tensile strength	MD/CMD	kN/m	9.5 / 9.5 SW	EN ISO 10319
	MD/CMD	kN/m	19 / 19 FW	EN ISO 10319
Elongation at peak	MD/CMD	%	40 / 50	EN ISO 10319
Static puncture resistance CBR		N	3000 -20% SW 4200 -20% FW	EN ISO 12236
Resistance to weathering	To be covered within 28 days			
Resistance to chemicals	Excellent			EN 14030
Design life	120 Years			Manufacturers declaration
Geotextile				
Thickness at 2kPa		mm	1.2 ±20%	EN ISO 9863-1
Tensile strength	MD/CMD	kN/m	9.5 -13%	EN ISO 10319
Pore size O ₉₀		µm	120 + 30%	EN ISO 12956
Water flow to 50mm head		l/m ² .s	115 + 30 %	EN ISO 11058
Static puncture resistance CBR		N	1600 -20%	EN ISO 12236
Dynamic perf cone drop		mm	32 + 20%	EN ISO 13433
Roll size	Width	m	0.915	
	Length	m	50	

NBS Specification:

PAG 25 Ventlayer is specified using the following:

Clause: J40/295

Product: PAG 25 Ventlayer

Supplier: PAGeoTechnical Ltd, Darwin House, Corby Gate Business Park, Corby, NN17 5JG.

Roll Sizing & Weight:

0.915m x 50m (45.75m²)

Roll weight – Single Wrap 80kg, Fully wrapped 87 kg - hence appropriate care and equipment is required for unloading and handling.

Storage and Handling:

Classified as non-hazardous when used in accordance with the relevant British Standards. The product is chemically inert and is not affected by acids and alkalis that may be present in the sub-soils.

Rolls are wrapped individually in polythene. Each roll bears a product description label. Rolls should be stored under cover and on a flat, level surface, and protected from mechanical damage and heat sources. During storage exposure to direct sunlight is to be avoided.

PAGeoTechnical Ltd. Darwin House, Corby Gate Business Park
Corby, Northants, NN17 5JG

Tel : 01536 740040 e-mail : office@pageo.co.uk web : www.pageo.co.uk
Registered in England and Wales No.4120437. Registered office as above.

