

Nicotarp[®] 7 Specification

TEST	UNIT	Nicotarp 7	TEST METHOD
Weight	g/m ²	214	EN 965
Thickness at 2kPa	mm	0.34	EN 964-1
Core material		HDPE	
Coating material		LDPE	
Tensile strength MD	kN/m	17	EN 13859
Tensile strength CD	kN/m	17	EN 13859
Elongation at break MD	%	28	EN 13859
Elongation at break CD	%	20	EN 13859
Length	m	50	
Width	m	6	
Diameter of roll	m	0.2	
Weight of roll	kg	39	

Nicotarp[®] 7 "P"

is a micro-perforated version of the material which allows moisture vapour to escape whilst maintaining complete water tightness.

Water Vapour Transmission	g/m ² /day	55.6	Lyssy (DIN53122)
Resistance to water penetration	ml	0	prEN13111

Jan 2017