

## Blackline 750 Specification

LDPE Geomembrane.

Product data	Monarflex® Blackline 750			
Composition: Top layer Coater layer Bottom layer	Black LDPE blown film Black LDPE Black LDPE blown film			
Colour	Black			
Application	100 -150 mm overlapping and either sealed with double-sided butyl tape or welded.			
Technical data	Unit	Value	Tolerance	Test method
Length	m	25	+1% -0%	EN 1848-2
Width	m	2 or 4	+1.5% -0,5%	EN 1848-2
Thickness	mm	0,75	+/- 10%	EN 1849-2
Weight	g/m <sup>2</sup>	700	+/- 5%	EN 1849-2
Weight per roll	kg	70 (4.0 x 25)		EN 1848-2
Tensile strength	kN/m	MD: 7.5 CD: 7.4		EN 12311-2
Elongation at break	%	MD: 500 CD: 500		EN 12311-2
Water tightness	kPa	20		EN 1928, Method B
Dimensional stability	%	Max 2	-0.9 / -0.1%	EN1107-2
Sd value	m	>150		EN 1931
Water vapour permeability	kg/(m <sup>2</sup> .s)	1.5x10 <sup>-9</sup>	+/- 25%	EN 1931
Tear resistance	N	300		EN 12310-1
Resistance to static loading	N	Pass at 200N		EN 12730, Method B
Temperature range	°C	-40 to 80		
Puncture resistance	N	270		FTMS-101C
Cold flexibility	°C	Pass at -30°C		MFX test
Bitumen compatibility	Pass/Fail	Pass class W1		EN 1548
Joint strength, tape	N/50mm	>60 N		EN 12317-2
Monarflex s.r.o., Továrenská 1, SK 943 03 Stúrovo, Slovakia 09 1162-CPD-0254				

Jan 2017